

Rec'd PCT/PTO 20 DEC 2004



Europäisches
Patentamt

European
Patent Office

Office européen
des brevets

REC'D 31 JUL 2003

WIPO

PCT

Bescheinigung

Certificate

Attestation

Die angehefteten Unterla-
gen stimmen mit der
ursprünglich eingereichten
Fassung der auf dem näch-
sten Blatt bezeichneten
europäischen Patentanmel-
dung überein.

The attached documents
are exact copies of the
European patent application
described on the following
page, as originally filed.

Les documents fixés à
cette attestation sont
conformes à la version
initialement déposée de
la demande de brevet
européen spécifiée à la
page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

02405514.7

**PRIORITY
DOCUMENT**
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

Der Präsident des Europäischen Patentamts;
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.

R C van Dijk

DEN HAAG, DEN
THE HAGUE,
LA HAYE, LE

27/03/03

BEST AVAILABLE COPY



Europäisches
Patentamt

European
Patent Office

Office européen
des brevets

Blatt 2 der Bescheinigung
Sheet 2 of the certificate
Page 2 de l'attestation

Anmeldung Nr.:
Application no.:
Demande n°: 02405514.7

Anmeldetag:
Date of filing:
Date de dépôt: 20/06/02

Anmelder:
Applicant(s):
Demandeur(s):
Ciba Specialty Chemicals Holding Inc.
4057 Basel
SWITZERLAND

Bezeichnung der Erfindung:
Title of the invention:
Titre de l'invention:

Grafting of nitroxyl terminated oligomers or polymers onto thermoplastic polymers

In Anspruch genommene Priorität(en) / Priority(ies) claimed / Priorité(s) revendiquée(s)

Staat:
State:
Pays:

Tag:
Date:
Date:

Aktenzeichen:
File no.
Numéro de dépôt:

Internationale Patentklassifikation:
International Patent classification:
Classification Internationale des brevets:
C08F4/00, C08G81/02

Am Anmeldetag benannte Vertragsstaaten:
Contracting states designated at date of filing:
Etats contractants désignés lors du dépôt:

AT/BE/CH/CY/DE/DK/ES/FI/FR/GB/GR/IE/IT/LI/LU/MC/NL/PT/SE/TR

Bemerkungen:
Remarks:
Remarques:

Grafting of Nitroxyl Terminated Oligomers or Polymers onto Thermoplastic Polymers

The instant invention relates to a process for the preparation of grafted polymers wherein in a first step A) a oligomer or polymer is prepared by controlled free radical polymerization in the presence of a stable free nitroxyl radical or a nitroxylether to obtain a nitroxyl terminated oligomer or polymer and in a second step B) the nitroxyl terminated oligomer or polymer is mixed and reacted with a thermoplastic or elastomeric polymer or copolymer in its molten state at a temperature at which cleavage of the nitroxyl-polymer/oligomer bond occurs, whereby the nitroxyl terminated oligomer or polymer is chemically bonded to the thermoplastic or elastomeric polymer. A further subject of the present invention is a grafted/comb polymer prepared by said process.

Increasing activities have been directed towards chemical modifications of existing polymers in order to obtain functional and/or engineered new materials. Chemical modifications of existing polymers are important for at least two reasons: 1. They can be an inexpensive and rapid way of obtaining new polymers without having to search for new monomers; 2. they may be the only way to synthesize polymers with the intended new characteristics.

An important chemical modification is the free radical grafting of functionalized or reactive monomers, which involves reaction of a polymer with a vinyl-group containing monomer or mixture of monomers capable of forming grafts onto the polymer backbone. If the grafts are long enough, the modified polymer has properties of a true graft copolymer, which will be different from those of the original polymer substrate. When the grafts are short with less than, for example five moieties, most of the physical and or mechanical properties of the modified polymer substrate will be retained. However, these changes can e.g. result in altered adhesion and surface properties or modified compatibilization behavior with other substrates

The advantages of free radical-grafting are further gained with the use of batch mixers or screw extruders as chemical reactors, which allow the free radical-grafting reaction to occur without solvents. This is for example described by G. H. Hu et al., in "Reactive Modifiers for Polymers", first edition, Blackie Academic & Professional an Imprint of Chapman & Hall, London 1997, chapter 1, pages 1-97.

These free radical-grafting reactions are usually performed in the presence of a free radical source such as a peroxide and a reactive monomer, such as for example acrylic acid. However the use of free radical sources such as peroxides may cause undesired side reactions leading to problems during synthesis and processing (gel formation, crosslinking, molecular weight reduction) or during use. Typically the long term stability is reduced and/or the polymer cannot anymore be used in outdoor applications or in applications at elevated temperatures.

By the instant invention the disadvantages of the prior art are avoided, by preparing in a first step a nitroxyl terminated oligomer or polymer, the molecular weight of which can be adjusted for example by the concentration of the nitroxyl compound, the monomer used, the reaction time and temperature. The nitroxyl terminated oligomer or polymer acts in a second step as a macroinitiator and the polymer radical derived from the macroinitiator is grafted onto the elastomeric or thermoplastic polymer or copolymer.

Another aspect subject of the invention is the manufacture of graft copolymers with a clearly defined structure, e.g. pre-defined and similar branches. The same type of graft copolymers, i.e. with clearly defined long chain branches, can hardly be achieved by standard grafting procedures due to uncontrollable side reactions and limited reaction times.

Processes for the preparation of nitroxyl terminated oligomers or polymers are known in the art.

For example US-A-4 581 429 to Solomon et al., issued April 8, 1986, discloses a free radical polymerization process which controls the growth of polymer chains to produce short chain or oligomeric homopolymers and copolymers. The process employs an initiator having the formula (in part) $R'R''N-O-X$, where X is a free radical species capable of polymerizing unsaturated monomers and the radical $R'R''N-O\bullet$ is terminating the growing oligomer/polymer.


US 5322912 to Georges et al. issued June 21, 1994 discloses a polymerization process using a free radical initiator, a polymerizable monomer compound and a stable free radical agent of the basic structure $R'R''N-O\bullet$ for the synthesis of homopolymers and block copolymers which are terminated by the nitroxyl radical.

More recently further nitroxyl radicals and nitroxyl ethers have been described.

WO 98/13392 for example describes open chain alkoxyamine compounds, which have a symmetrical substitution pattern and are derived from NO gas or from nitroso compounds.

WO 96/24620 describes a polymerization process in which very specific stable free radical

agents are used, such as for example



WO 98/30601 discloses specific nitroxyls based on imidazolidinons.

WO 98/44008 discloses specific nitroxyls based on morpholinones, piperazinones and piperazindiones.

These prior art nitroxyl radicals and nitroxyl ethers are all suitable for the instant process.

The instant invention relates to a process for the preparation of a grafted thermoplastic or elastomeric polymer or copolymer, which process comprises in a first step

A) the preparation of a nitroxyl terminated oligomer or polymer by controlled free radical polymerization of an ethylenically unsaturated monomer

a1) in the presence of a nitroxyl ether $R'R''N-O-X$ wherein X is selected such, that cleavage of the $O-X$ bond occurs and a radical $X\bullet$ is formed capable of initiating polymerization; or

a2) in the presence of a nitroxyl radical $R'R''N-O\bullet$ and a free radical initiator capable of initiating polymerization; and in a second step

B) heating, mixing and reacting the nitroxyl terminated oligomer or polymer of step A) together with a thermoplastic or elastomeric polymer or copolymer in the molten state at a temperature of between 150°C and 300°C .

Suitable thermoplastic or elastomeric polymers and copolymers are subsequently mentioned.

1. Polymers of monoolefins and diolefins, for example polypropylene, polyisobutylene, polybut-1-ene, poly-4-methylpent-1-ene, polyvinylcyclohexane, polyisoprene or polybutadiene,

as well as polymers of cycloolefins, for instance of cyclopentene or norbornene, polyethylene (which optionally can be crosslinked), for example high density polyethylene (HDPE), high density and high molecular weight polyethylene (HDPE-HMW), high density and ultrahigh molecular weight polyethylene (HDPE-UHMW), medium density polyethylene (MDPE), low density polyethylene (LDPE), linear low density polyethylene (LLDPE), (VLDPE) and (ULDPE).

Polyolefins, i.e. the polymers of monoolefins exemplified in the preceding paragraph, preferably polyethylene and polypropylene, can be prepared by different, and especially by the following, methods:

- a) radical polymerisation (normally under high pressure and at elevated temperature).
 - b) catalytic polymerisation using a catalyst that normally contains one or more than one metal of groups IVb, Vb, VIb or VIII of the Periodic Table. These metals usually have one or more than one ligand, typically oxides, halides, alcoholates, esters, ethers, amines, alkyls, alkenyls and/or aryls that may be either π - or σ -coordinated. These metal complexes may be in the free form or fixed on substrates, typically on activated magnesium chloride, titanium(III) chloride, alumina or silicon oxide. These catalysts may be soluble or insoluble in the polymerisation medium. The catalysts can be used by themselves in the polymerisation or further activators may be used, typically metal alkyls, metal hydrides, metal alkyl halides, metal alkyl oxides or metal alkyloxanes, said metals being elements of groups Ia, IIa and/or IIIa of the Periodic Table. The activators may be modified conveniently with further ester, ether, amine or silyl ether groups. These catalyst systems are usually termed Phillips, Standard Oil Indiana, Ziegler (-Natta), TNZ (DuPont), metallocene or single site catalysts (SSC).
2. Mixtures of the polymers mentioned under 1), for example mixtures of polypropylene with polyisobutylene, polypropylene with polyethylene (for example PP/HDPE, PP/LDPE) and mixtures of different types of polyethylene (for example LDPE/HDPE).
 3. Copolymers of monoolefins and diolefins with each other or with other vinyl monomers, for example ethylene/propylene copolymers, linear low density polyethylene (LLDPE) and

mixtures thereof with low density polyethylene (LDPE), propylene/but-1-ene copolymers, propylene/isobutylene copolymers, ethylene/but-1-ene copolymers, ethylene/hexene copolymers, ethylene/methylpentene copolymers, ethylene/heptene copolymers, ethylene/octene copolymers, ethylene/vinylcyclohexane copolymers, ethylene/cycloolefin copolymers (e.g. ethylene/norbornene like COC), ethylene/1-olefins copolymers, where the 1-olefin is generated in-situ; propylene/butadiene copolymers, isobutylene/isoprene copolymers, ethylene/vinylcyclohexene copolymers, ethylene/alkyl acrylate copolymers, ethylene/alkyl methacrylate copolymers, ethylene/vinyl acetate copolymers or ethylene/acrylic acid copolymers and their salts (ionomers) as well as terpolymers of ethylene with propylene and a diene such as hexadiene, dicyclopentadiene or ethylidene-norbornene; and mixtures of such copolymers with one another and with polymers mentioned in 1) above, for example polypropylene/ethylene-propylene copolymers, LDPE/ethylene-vinyl acetate copolymers (EVA), LDPE/ethylene-acrylic acid copolymers (EAA), LLDPE/EVA, LLDPE/EAA and alternating or random polyalkylene/carbon monoxide copolymers and mixtures thereof with other polymers, for example polyamides.

4. Hydrocarbon resins (for example C_5-C_9) including hydrogenated modifications thereof (e.g. tackifiers) and mixtures of polyalkylenes and starch.

Homopolymers and copolymers from 1.) - 4.) may have any stereostructure including syndiotactic, isotactic, hemi-isotactic or atactic; where atactic polymers are preferred. Stereoblock polymers are also included.

5. Polystyrene, poly(p-methylstyrene), poly(α -methylstyrene).

6. Aromatic homopolymers and copolymers derived from vinyl aromatic monomers including styrene, α -methylstyrene, all isomers of vinyl toluene, especially p-vinyltoluene, all isomers of ethyl styrene, propyl styrene, vinyl biphenyl, vinyl naphthalene, and vinyl anthracene, and mixtures thereof. Homopolymers and copolymers may have any stereostructure including syndiotactic, isotactic, hemi-isotactic or atactic; where atactic polymers are preferred. Stereoblock polymers are also included.

6a. Copolymers including aforementioned vinyl aromatic monomers and comonomers selected from ethylene, propylene, dienes, nitriles, acids, maleic anhydrides, maleimides, vinyl

acetate and vinyl chloride or acrylic derivatives and mixtures thereof, for example styrene/butadiene, styrene/acrylonitrile, styrene/ethylene (interpolymers), styrene/alkyl methacrylate, styrene/butadiene/alkyl acrylate, styrene/butadiene/alkyl methacrylate, styrene/maleic anhydride, styrene/acrylonitrile/methyl acrylate; mixtures of high impact strength of styrene copolymers and another polymer, for example a polyacrylate, a diene polymer or an ethylene/propylene/diene terpolymer; and block copolymers of styrene such as styrene/butadiene/styrene, styrene/isoprene/styrene, styrene/ethylene/butylene/styrene or styrene/ethylene/propylene/styrene.

6b. Hydrogenated aromatic polymers derived from hydrogenation of polymers mentioned under 6.), especially including polycyclohexylethylene (PCHE) prepared by hydrogenating atactic polystyrene, often referred to as polyvinylcyclohexane (PVCH).

6c. Hydrogenated aromatic polymers derived from hydrogenation of polymers mentioned under 6a.).

Homopolymers and copolymers may have any stereostructure including syndiotactic, isotactic, hemi-isotactic or atactic; where atactic polymers are preferred. Stereoblock polymers are also included.

7. Graft copolymers of vinyl aromatic monomers such as styrene or α -methylstyrene, for example styrene on polybutadiene, styrene on polybutadiene-styrene or polybutadiene-acrylonitrile copolymers; styrene and acrylonitrile (or methacrylonitrile) on polybutadiene; styrene, acrylonitrile and methyl methacrylate on polybutadiene; styrene and maleic anhydride on polybutadiene; styrene, acrylonitrile and maleic anhydride or maleimide on polybutadiene; styrene and maleimide on polybutadiene; styrene and alkyl acrylates or methacrylates on polybutadiene; styrene and acrylonitrile on ethylene/propylene/diene terpolymers; styrene and acrylonitrile on polyalkyl acrylates or polyalkyl methacrylates, styrene and acrylonitrile on acrylate/butadiene copolymers, as well as mixtures thereof with the copolymers listed under 6), for example the copolymer mixtures known as ABS, MBS, ASA or AES polymers.

8. Halogen-containing polymers such as polychloroprene, chlorinated rubbers, chlorinated and brominated copolymer of isobutylene-isoprene (halobutyl rubber), chlorinated or sulfochlorinated polyethylene, copolymers of ethylene and chlorinated ethylene, epichlorohydrin

homo- and copolymers, especially polymers of halogen-containing vinyl compounds, for example polyvinyl chloride, polyvinylidene chloride, polyvinyl fluoride, polyvinylidene fluoride, as well as copolymers thereof such as vinyl chloride/vinylidene chloride, vinyl chloride/vinyl acetate or vinylidene chloride/vinyl acetate copolymers.

9. Polymers derived from α,β -unsaturated acids and derivatives thereof such as polyacrylates and polymethacrylates; polymethyl methacrylates, polyacrylamides and polyacrylonitriles, impact-modified with butyl acrylate.

10. Copolymers of the monomers mentioned under 9) with each other or with other unsaturated monomers, for example acrylonitrile/ butadiene copolymers, acrylonitrile/alkyl acrylate copolymers, acrylonitrile/alkoxyalkyl acrylate or acrylonitrile/vinyl halide copolymers or acrylonitrile/ alkyl methacrylate/butadiene terpolymers.

11. Polymers derived from unsaturated alcohols and amines or the acyl derivatives or acetals thereof, for example polyvinyl alcohol, polyvinyl acetate, polyvinyl stearate, polyvinyl benzoate, polyvinyl maleate, polyvinyl butyral, polyallyl phthalate or polyallyl melamine; as well as their copolymers with olefins mentioned in 1) above.

12. Homopolymers and copolymers of cyclic ethers such as polyalkylene glycols, polyethylene oxide, polypropylene oxide or copolymers thereof with bisglycidyl ethers.

13. Polyacetals such as polyoxymethylene and those polyoxymethylenes which contain ethylene oxide as a comonomer; polyacetals modified with thermoplastic polyurethanes, acrylates or MBS.

14. Polyphenylene oxides and sulfides, and mixtures of polyphenylene oxides with styrene polymers or polyamides.

15. Polyurethanes derived from hydroxyl-terminated polyethers, polyesters or polybutadienes on the one hand and aliphatic or aromatic polyisocyanates on the other, as well as precursors thereof.

16. Polyamides and copolyamides derived from diamines and dicarboxylic acids and/or from aminocarboxylic acids or the corresponding lactams, for example polyamide 4, polyamide 6, polyamide 6/6, 6/10, 6/9, 6/12, 4/6, 12/12, polyamide 11, polyamide 12, aromatic polyamides starting from m-xylene diamine and adipic acid; polyamides prepared from hexamethylenediamine and isophthalic or/and terephthalic acid and with or without an elastomer as modifier, for example poly-2,4,4,-trimethylhexamethylene terephthalamide or poly-m-phenylene isophthalamide; and also block copolymers of the aforementioned polyamides with polyolefins, olefin copolymers, ionomers or chemically bonded or grafted elastomers; or with polyethers, e.g. with polyethylene glycol, polypropylene glycol or polytetramethylene glycol; as well as polyamides or copolyamides modified with EPDM or ABS; and polyamides condensed during processing (RIM polyamide systems).

17. Polyureas, polyimides, polyamide-imides, polyetherimids, polyesterimids, polyhydantoins and polybenzimidazoles.

18. Polyesters derived from dicarboxylic acids and diols and/or from hydroxycarboxylic acids or the corresponding lactones, for example polyethylene terephthalate, polybutylene terephthalate, poly-1,4-dimethylolcyclohexane terephthalate, polyalkylene naphthalate (PAN) and polyhydroxybenzoates, as well as block copolyether esters derived from hydroxyl-terminated polyethers; and also polyesters modified with polycarbonates or MBS.

19. Polycarbonates and polyester carbonates.

20. Polyketones.

21. Polysulfones, polyether sulfones and polyether ketones.


22. Blends of the aforementioned polymers (polyblends), for example PP/EPDM, Polyamide/EPDM or ABS, PVC/EVA, PVC/ABS, PVC/MBS, PC/ABS, PBTP/ABS, PC/ASA, PC/PBT, PVC/CPE, PVC/acrylates, POM/thermoplastic PUR, PC/thermoplastic PUR, POM/acrylate, POM/MBS, PPO/HIPS, PPO/PA 6.6 and copolymers, PA/HDPE, PA/PP, PA/PPO, PBT/PC/ABS or PBT/PET/PC.

Preferably the thermoplastic or elastomeric polymer or copolymer is selected from the group consisting of a polyolefin and its copolymers, polystyrene and its block or graft copolymers and polymers or copolymers derived from 1,3-dienes.



More preferably the thermoplastic or elastomeric polymer or copolymer is selected from the group consisting of low density polyethylene (LDPE, LLDPE), high density polyethylene (HDPE), polypropylene (PP), polystyrene (PS), styrene-block copolymers (SI(S), SI, SB(S), ABS ASA), ethylene-propylene-diene modified rubber (EPDM, EPM) and ethylene propylene rubber (EPR), polybutylene (PB), polyisobutylene (PIB), poly-4-methylpentene-1 (PMP).

In a specific embodiment of the invention the thermoplastic or elastomeric polymer or copolymer contains unsaturated bonds.

Typically X is selected from the group consisting of



$\text{C}_6\text{cycloalkyl})_2\text{CCN}$, $(\text{C}_1\text{-C}_{12}\text{alkyl})_2\text{CCN}$, $-\text{CH}_2\text{CH}=\text{CH}_2$, $(\text{C}_1\text{-C}_{12})\text{alkyl-CR}_{20}\text{-C(O)-}(\text{C}_1\text{-C}_{12})\text{alkyl}$, $(\text{C}_1\text{-C}_{12})\text{alkyl-CR}_{20}\text{-C(O)-}(\text{C}_6\text{-C}_{10})\text{aryl}$, $(\text{C}_1\text{-C}_{12})\text{alkyl-CR}_{20}\text{-C(O)-}(\text{C}_1\text{-C}_{12})\text{alkoxy}$, $(\text{C}_1\text{-C}_{12})\text{alkyl-CR}_{20}\text{-C(O)-phenoxy}$, $(\text{C}_1\text{-C}_{12})\text{alkyl-CR}_{20}\text{-C(O)-N-di}(\text{C}_1\text{-C}_{12})\text{alkyl}$, $(\text{C}_1\text{-C}_{12})\text{alkyl-CR}_{20}\text{-CO-NH}(\text{C}_1\text{-C}_{12})\text{alkyl}$, $(\text{C}_1\text{-C}_{12})\text{alkyl-CR}_{20}\text{-CO-NH}_2$, $-\text{CH}_2\text{CH}=\text{CH-CH}_3$, $-\text{CH}_2\text{-C}(\text{CH}_3)=\text{CH}_2$,




R_{20} is hydrogen or $\text{C}_1\text{-C}_{12}\text{alkyl}$;

the alkyl groups are unsubstituted or substituted with one or more $-\text{OH}$, $-\text{COOH}$ or $-\text{C(O)R}_{20}$ groups; and


the aryl groups are phenyl or naphthyl which are unsubstituted or substituted with C₁-C₁₂alkyl, halogen, C₁-C₁₂alkoxy, C₁-C₁₂alkylcarbonyl, glycidyloxy, OH, -COOH or -COO(C₁-C₁₂)alkyl.

The nitroxylethers and nitroxyl radicals suitable for the invention are principally known from US-A-4 581 429 or EP-A-621 878. Particularly useful are the open chain compounds described in WO 98/13392, WO 99/03894 and WO 00/07981, the piperidine derivatives described in WO 99/67298, GB 2335190 and GB 2 361 235 or the heterocyclic compounds described in GB 2342649 and WO 96/24620. Recently further nitroxyl radicals and nitroxyl ethers have been described in International Applications No. PCT/EP01/13072, PCT/EP01/13071 and European Application No. EP 01811154.2 . Some compounds are commercially available or can be prepared according to the aforementioned documents.

In a specific embodiment of the invention the nitroxyl-ether or the nitroxyl radical contains a structural element of formula (Ia) or (Ib)



(Ia),








(Ib) wherein

G₁, G₂, G₃, G₄ are independently C₁-C₆alkyl or G₁ and G₂ or G₃ and G₄, or G₁ and G₂ and G₃ and G₄ together form a C₅-C₁₂cycloalkyl group;


G₅, G₆ independently are H, C₁-C₁₈alkyl, phenyl, naphthyl or a group COOC₁-C₁₈alkyl.

In one embodiment of the invention components a1) and a2) are of formula A, A', B, B' or O, O'





(O)



(O')

wherein

G_1 , G_2 , G_3 and G_4 are independently alkyl of 1 to 4 carbon atoms, or G_1 and G_2 together and G_3 and G_4 together, or G_1 and G_2 together or G_3 and G_4 together are pentamethylene;

G_5 and G_6 are independently hydrogen or C_1 - C_4 alkyl;

m is 1, 2, 3 or 4

R , if m is 1, is hydrogen, C_1 - C_{18} alkyl which is uninterrupted or C_2 - C_{18} alkyl which is interrupted by one or more oxygen atoms, cyanoethyl, benzoyl, glycidyl, a monovalent radical of an aliphatic carboxylic acid having 2 to 18 carbon atoms, of a cycloaliphatic carboxylic acid having 7 to 15 carbon atoms, or an α,β -unsaturated carboxylic acid having 3 to 5 carbon atoms or of an aromatic carboxylic acid having 7 to 15 carbon atoms, where each carboxylic acid can be substituted in the aliphatic, cycloaliphatic or aromatic moiety by 1 to 3 $-COOZ_{12}$ groups, in which Z_{12} is H, C_1 - C_{20} alkyl, C_3 - C_{12} alkenyl, C_5 - C_7 cycloalkyl, phenyl or benzyl; or R is a monovalent radical of a carbamic acid or phosphorus-containing acid or a monovalent silyl radical;

R , if m is 2, is C_2 - C_{12} alkylene, C_4 - C_{12} alkenylene, xylylene, a divalent radical of an aliphatic dicarboxylic acid having 2 to 36 carbon atoms, or a cycloaliphatic or aromatic dicarboxylic acid having 8-14 carbon atoms or of an aliphatic, cycloaliphatic or aromatic dicarbamic acid having 8-14 carbon atoms, where each dicarboxylic acid may be substituted in the aliphatic, cycloaliphatic or aromatic moiety by one or two $-COOZ_{12}$ groups; or

R is a divalent radical of a phosphorus-containing acid or a divalent silyl radical;

R , if m is 3, is a trivalent radical of an aliphatic, cycloaliphatic or aromatic tricarboxylic acid, which may be substituted in the aliphatic, cycloaliphatic or aromatic moiety by $-COOZ_{12}$, of an aromatic tricarbamic acid or of a phosphorus-containing acid, or is a trivalent silyl radical,

R , if m is 4, is a tetravalent radical of an aliphatic, cycloaliphatic or aromatic tetracarboxylic acid;

p is 1, 2 or 3,

R_{101} is C_1 - C_{12} alkyl, C_5 - C_7 cycloalkyl, C_7 - C_9 phenylalkyl, C_2 - C_{18} alkanoyl, C_3 - C_5 alkenoyl or benzoyl;


when p is 1,

R_{102} is C_1 - C_{18} alkyl, C_5 - C_7 cycloalkyl, C_2 - C_8 alkenyl unsubstituted or substituted by a cyano, carbonyl or carbamide group, or is glycidyl, a group of the formula $-CH_2CH(OH)-Z$ or of the formula $-CO-Z-$ or $-CONH-Z$ wherein Z is hydrogen, methyl or phenyl; or

when p is 2,

R_{102} is C_2 - C_{12} alkylene, C_6 - C_{12} -arylene, xylylene, a $-CH_2CH(OH)CH_2-O-B-O-CH_2CH(OH)CH_2-$ group, wherein B is C_2 - C_{10} alkylene, C_6 - C_{16} arylene or C_6 - C_{12} cycloalkylene; or, provided that R_{101} is not alkanoyl, alkenoyl or benzoyl, R_{102} can also be a divalent acyl radical of an aliphatic, cycloaliphatic or aromatic dicarboxylic acid or dicarbamic acid, or can be the group $-CO-$; or R_{101} and R_{102} together when p is 1 can be the cyclic acyl radical of an aliphatic or aromatic 1,2- or 1,3-dicarboxylic acid; or

R_{102} is a group







where T_7 and T_8 are independently hydrogen, alkyl of 1 to 18 carbon atoms, or T_7 and T_8 together are alkylene of 4 to 6 carbon atoms or 3-oxapentamethylene;


when p is 3,

R_{102} is 2,4,6-triazinyl ; and

X is as defined above.

Preferably component a1) and a2) are of formula A, A', B, B' or O, O'





wherein

m is 1,

R is hydrogen, C₁-C₁₈alkyl which is uninterrupted or interrupted by one or more oxygen atoms, cyanoethyl, benzoyl, glycidyl, a monovalent radical of an aliphatic carboxylic acid having 2 to 18 carbon atoms, of a cycloaliphatic carboxylic acid having 7 to 15 carbon atoms, or an α,β -unsaturated carboxylic acid having 3 to 5 carbon atoms or of an aromatic carboxylic acid having 7 to 15 carbon atoms;

p is 1;

R₁₀₁ is C₁-C₁₂alkyl, C₅-C₇cycloalkyl, C₇-C₈aralkyl, C₂-C₁₈alkanoyl, C₃-C₅alkenoyl or benzoyl;

R₁₀₂ is C₁-C₁₈alkyl, C₅-C₇cycloalkyl, C₂-C₈alkenyl unsubstituted or substituted by a cyano, carbonyl or carbamide group, or is glycidyl, a group of the formula -CH₂CH(OH)-Z or of the formula -CO-Z or -CONH-Z wherein Z is hydrogen, methyl or phenyl;

G₆ is hydrogen and G₅ is hydrogen or C₁-C₄alkyl,

G₁, G₂, G₃ and G₄ are methyl; or

G₁ and G₃ are methyl and G₂ and G₄ are ethyl or propyl or G₁ and G₂ are methyl and G₃ and G₄ are ethyl or propyl; and

X is selected from the group consisting of

-CH₂-phenyl, CH₃CH-phenyl, (CH₃)₂C-phenyl, (C₅-C₈cycloalkyl)₂CCN, (CH₃)₂CCN, -CH₂CH=CH₂, CH₃CH-CH=CH₂ (C₁-C₄alkyl)CR₂₀-C(O)-phenyl, (C₁-C₄)alkyl-CR₂₀-C(O)-(C₁-C₄)alkoxy, (C₁-C₄)alkyl-CR₂₀-C(O)-(C₁-C₄)alkyl, (C₁-C₄)alkyl-CR₂₀-C(O)-N-di(C₁-C₄)alkyl, (C₁-C₄)alkyl-CR₂₀-C(O)-NH(C₁-C₄)alkyl, (C₁-C₄)alkyl-CR₂₀-C(O)-NH₂, wherein

R₂₀ is hydrogen or (C₁-C₄)alkyl.

In a particularly preferred process G₂ and G₄ are ethyl, G₁ and G₃ are methyl, G₆ is hydrogen and G₅ is methyl.

The alkyl radicals in the various substituents may be linear or branched. Examples of alkyl containing 1 to 20 carbon atoms are methyl, ethyl, propyl, isopropyl, butyl, 2-butyl, isobutyl, t-butyl, pentyl, 2-pentyl, hexyl, heptyl, octyl, 2-ethylhexyl, t-octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, hexadecyl and octadecyl.

Alkenyl with 3 to 18 carbon atoms is a linear or branched radical as for example propenyl, 2-butenyl, 3-butenyl, isobutenyl, n-2,4-pentadienyl, 3-methyl-2-butenyl, n-2-octenyl, n-2-dodecenyl, iso-dodecenyl, oleyl, n-2-octadecenyl oder n-4-octadecenyl.

Preferred is alkenyl with 3 bis 12, particularly preferred with 3 to 6 carbon atoms.

C₂-C₁₈alkyl interrupted by at least one O atom is for example -CH₂-CH₂-O-CH₂-CH₃, -CH₂-CH₂-O-CH₃- or -CH₂-CH₂-O-CH₂-CH₂-CH₂-O-CH₂-CH₃-. It is preferably derived from polyethylene glycol. A general description is -((CH₂)_a-O)_b-H/CH₃, wherein a is a number from 1 to 6 and b is a number from 2 to 10.

C₃-C₁₂cycloalkyl is typically, cyclopropyl, cyclopentyl, methylcyclopentyl, dimethylcyclopentyl, cyclohexyl, methylcyclohexyl or trimethylcyclohexyl.

C₆-C₁₀ aryl is for example phenyl or naphthyl, but also comprised are C₁-C₄alkyl substituted phenyl, C₁-C₄alkoxy substituted phenyl, hydroxy, halogen or nitro substituted phenyl. Examples for alkyl substituted phenyl are ethylbenzene, toluene, xylene and its isomers, mesitylene or isopropylbenzene. Halogen substituted phenyl is for example dichlorobenzene or bromotoluene. Examples for C₆-C₁₂arylene can be derived from the above.

Alkoxy substituents are typically methoxy, ethoxy, propoxy or butoxy and their corresponding isomers.

C₇-C₉phenylalkyl is benzyl, phenylethyl or phenylpropyl.

When R is a monovalent radical of a carboxylic acid, R is, for example, an acetic acid, caproic acid, stearic acid, acrylic acid, methacrylic acid, benzoic acid or β-(3,5-di-tert-butyl-4-hydroxy-phenyl)-propionic acid radical.

When R is a monovalent silyl radical, Z_{12} is, for example, a radical of formula $-(C_jH_{2j})-Si(Z')_2Z''$ wherein j is an integer from the range 2 to 5 and Z' and Z'' are each independently of the other C_1 - C_4 alkyl or C_1 - C_4 alkoxy.

When R is a bivalent radical of a dicarboxylic acid, R is, for example, a malonic acid, succinic acid, glutaric acid, adipic acid, suberic acid, sebacic acid, maleic acid, itaconic acid, phthalic acid, dibutylmalonic acid, dibenzylmalonic acid, butyl-(3,5-di-tert-butyl-4-hydroxybenzyl)-malonic acid or bicycloheptenedicarboxylic acid radical.


When R is a trivalent radical of a tricarboxylic acid, R is, for example, a trimellitic acid, citric acid or nitrilotriacetic acid radical.

When R is a tetravalent radical of a tetracarboxylic acid, R is, for example, the tetravalent radical of butane-1,2,3,4-tetracarboxylic acid or of pyromellitic acid.

When R is a bivalent radical of a dicarbamic acid, R is, for example, a hexamethylene-dicarbamic acid or 2,4-toluylene-dicarbamic acid radical.


C_1 - C_{18} alkanoyl is for example, formyl, propionyl, butyryl, octanoyl, dodecanoyl but preferably acetyl and C_3 - C_5 alkenoyl is in particular acryloyl.

Particularly suitable nitroxylethers and nitroxyl radicals are those of formulae





1



The free radical initiator of component a2) is preferably a bis-azo compound, a peroxide, a perester or a hydroperoxide.

Specific preferred radical sources are 2,2'-azobisisobutyronitrile, 2,2'-azobis(2-methylbutyronitrile), 2,2'-azobis(2,4-dimethylvaleronitrile), 2,2'-azobis(4-methoxy-2,4-dimethylvaleronitrile), 1,1'-azobis(1-cyclohexanecarbonitrile), 2,2'-azobis(isobutyramide) dihydrate, 2-phenylazo-2,4-dimethyl-4-methoxyvaleronitrile, dimethyl-2,2'-azobisisobutyrate, 2-(carbamoylazo)isobutyronitrile, 2,2'-azobis(2,4,4-trimethylpentane), 2,2'-azobis(2-methylpropane), 2,2'-azobis(N,N'-dimethyleneisobutyramidine), free base or hydrochloride, 2,2'-azobis(2-amidinopropane), free base or hydrochloride, 2,2'-azobis{2-methyl-N-[1,1-bis(hydroxymethyl)ethyl]propionamide} or 2,2'-azobis{2-methyl-N-[1,1-bis(hydroxymethyl)-2-hydroxyethyl]propionamide; acetyl cyclohexane sulphonyl peroxide, diisopropyl peroxy dicarbonate, t-amyl perneodecanoate, t-butyl perneodecanoate, t-butyl perpivalate, t-amylperpivalate, bis(2,4-dichlorobenzoyl)peroxide, diisononanoyl peroxide, didecanoyl peroxide, dioctanoyl peroxide, dilauroyl peroxide, bis (2-methylbenzoyl) peroxide, disuccinic acid peroxide, diacetyl peroxide, dibenzoyl peroxide, t-butyl per 2-ethylhexanoate, bis-(4-chlorobenzoyl)-peroxide, t-butyl perisobutyrate, t-butyl permaleinate, 1,1-bis(t-butylperoxy)3,5,5-trimethylcyclohexane, 1,1-bis(t-butylperoxy)cyclohexane, t-butyl peroxy

isopropyl carbonate, t-butyl perisononaoate, 2,5-dimethylhexane 2,5-dibenzoate, t-butyl peracetate, t-amyl perbenzoate, t-butyl perbenzoate, 2,2-bis (t-butylperoxy) butane, 2,2 bis (t-butylperoxy) propane, dicumyl peroxide, 2,5-dimethylhexane-2,5-di-t-butylperoxide, 3-t-butylperoxy 3-phenylphthalide, di-t-amyl peroxide, α , α' -bis(t-butylperoxy isopropyl) benzene, 3,5-bis (t-butylperoxy)3,5-dimethyl 1,2-dioxolane, di-t-butyl peroxide, 2,5-dimethylhexyne-2,5-di-t-butylperoxide, 3,3,6,6,9,9-hexamethyl 1,2,4,5-tetraoxa cyclononane, p-menthane hydroperoxide, pinane hydroperoxide, diisopropylbenzene mono- α -hydroperoxide, cumene hydroperoxide or t-butyl hydroperoxide.

Azo initiators and peroxides are most preferred.

Preferably the nitroxylether of component a1) or the nitroxyl radical of component a2) is present in an amount of from 0.001 mol-% to 20 mol-%, more preferably of from 0.01 mol-% to 10 mol-% and most preferably of from 0.1 mol-% to 5 mol-%, based on the monomer or monomer mixture.

When monomer mixtures are used mol-% is calculated on an average molecular weight.

The free radical initiator is preferably present in an amount of from 0.001 mol-% to 20 mol-%, more preferably of from 0.01 mol-% to 10 mol-% and most preferably of from 0.1 mol-% to 5 mol-%, based on the monomer or monomer mixture.

The molar ratio of free radical initiator to stable free nitroxyl radical is preferably from 20:1 to 1:2, more preferably from 10:1 to 1:2.

Preferably the ethylenically unsaturated monomer or oligomer is selected from the group consisting of styrene, substituted styrene, conjugated dienes, vinyl acetate, vinylpyrrolidone, vinylimidazole, maleic anhydride, (alkyl)acrylic acidanhydrides, (alkyl)acrylic acid salts, (alkyl)acrylic esters, (meth)acrylonitriles, (alkyl)acrylamides, vinyl halides or vinylidene halides.

Preferably the ethylenically unsaturated monomer is a compound of formula $\text{CH}_2=\text{C}(\text{R}_a)-(\text{C}=\text{Z})-\text{R}_b$, wherein R_a is hydrogen or $\text{C}_1\text{-C}_4$ alkyl, R_b is NH_2 , $\text{O}^+(\text{Me}^+)$, glycidyl, unsubstituted $\text{C}_1\text{-C}_{18}$ alkoxy, $\text{C}_2\text{-C}_{100}$ alkoxy interrupted by at least one N and/or O atom, or

hydroxy-substituted C₁-C₁₈alkoxy, unsubstituted C₁-C₁₈alkylamino, di(C₁-C₁₈alkyl)amino, hydroxy-substituted C₁-C₁₈alkylamino or hydroxy-substituted di(C₁-C₁₈alkyl)amino, -O-CH₂-CH₂-N(CH₃)₂ or -O-CH₂-CH₂-N⁺H(CH₃)₂ An⁻;


An⁻ is an anion of a monovalent organic or inorganic acid;

Me is a monovalent metal atom or the ammonium ion.


Z is oxygen or sulfur.

Examples of acids from which the anion An⁻ is derived are C₁-C₁₂carboxylic acids, organic sulfonic acids such as CF₃SO₃H or CH₃SO₃H, mineralic acids such as HCl, HBr or HI, oxo acids such as HClO₄ or complex acids such as HPF₆ or HBF₄.

Examples for R_a as C₂-C₁₀₀alkoxy interrupted by at least one O atom are of formula










Further examples of suitable acrylate or methacrylate monomers are given below.





and R_a have the meaning as defined above and R_e is methyl or benzyl. An⁻ is preferably Cl⁻, Br⁻ or ⁻O₃S-CH₃.

Further acrylate monomers are



Examples for suitable monomers other than acrylates are



Preferably R_a is hydrogen or methyl, R_b is NH_2 , glycidyl, unsubstituted or with hydroxy substituted C_1 - C_4 alkoxy, unsubstituted C_1 - C_4 alkylamino, di(C_1 - C_4 alkyl)amino, hydroxy-substituted C_1 - C_4 alkylamino or hydroxy-substituted di(C_1 - C_4 alkyl)amino; and

Z is oxygen.

More preferred the ethylenically unsaturated monomer is an acrylic acid ester, acrylamide, acrylonitrile, methacrylic acid ester, methacrylamide, methacrylonitrile, maleic acid anhydride or styrene.

Acrylic acid esters and methacrylic acid esters are typically C₁-C₁₈alkyl esters.

Step A) of the instant process can also be carried out with a mixture of monomers, resulting in a nitroxyl terminated random copolymer. It is, however, also possible to carry out step A) in a consecutive way with different monomers, resulting in a block copolymer. The resulting macroinitiator can therefore be a homopolymer, a random copolymer containing two or more different monomers or a block copolymer, which may be a diblock, a triblock or a multiblock copolymer. The second monomer can also be added when still the first monomer is present in order to form tapered structures.

Block copolymers are, for example, block copolymers of polystyrene and polyacrylate (e.g., poly(styrene-co-acrylate) or poly(styrene-co-acrylate-co-styrene).

The scission of the O-C bond can be effected by ultrasonic treatment, heating or exposure to electromagnetic radiation, ranging from γ to microwaves.

The scission of the O-X bond is preferably effected by heating and takes place at a temperature of between 50°C and 180°C, more preferably from 80° C to 145° C.

The reaction temperature for step A) is typically between 50° C and 180° C, more preferably between 80° C and 145° C. Controlled polymerization is usually carried out under normal pressure. It is, however, possible for example when polymerization is carried out in the presence of water that a pressure from 1 bar to 20 bar is applied.

The reaction time for step A) can vary from several minutes to some hours, depending on the desired degree of monomer to polymer conversion, the monomer itself, reaction temperature and the desired molecular weight. Typical are 30 minutes to 24 hours, in particular 1 hour to 12 hours.

The nitroxyl terminated oligomer or polymer of step A) can be isolated and purified according to standard procedures of polymer chemistry. Preferably not reacted monomers are removed, so that the macroinitiator is essentially free of monomer when step B) is applied. The drying temperature should be below 100° C to avoid O-R bond cleavage. At ambient temperature the macroinitiator can be stored for a long time without losing its activity.

The process step A) may be carried out in the presence of an organic solvent or in the presence of water or in mixtures of organic solvents and water. Additional cosolvents or surfactants, such as glycols or ammonium salts of fatty acids, may be present. Other suitable cosolvents are described hereinafter.

If organic solvents are used, suitable solvents or mixtures of solvents are typically pure alkanes (hexane, heptane, octane, isooctane), aromatic hydrocarbons (benzene, toluene, xylene), halogenated hydrocarbons (chlorobenzene), alkanols (methanol, ethanol, ethylene glycol, ethylene glycol monomethyl ether), esters (ethyl acetate, propyl, butyl or hexyl acetate) and ethers (diethyl ether, dibutyl ether, ethylene glycol dimethyl ether), or mixtures thereof.

The aqueous polymerization reactions can be supplemented with a water-miscible or hydrophilic cosolvent to help ensure that the reaction mixture remains a homogeneous single phase throughout the monomer conversion. Any water-soluble or water-miscible cosolvent may be used, as long as the aqueous solvent medium is effective in providing a solvent system which prevents precipitation or phase separation of the reactants or polymer products until after all polymerization reactions have been completed. Exemplary cosolvents useful in the present invention may be selected from the group consisting of aliphatic alcohols, glycols, ethers, glycol ethers, pyrrolidines, N-alkyl pyrrolidinones, N-alkyl pyrrolidones, polyethylene glycols, polypropylene glycols, amides, carboxylic acids and salts thereof, esters, organosulfides, sulfoxides, sulfones, alcohol derivatives, hydroxyether derivatives such as butyl carbitol or cellosolve, amino alcohols, ketones, and the like, as well as derivatives thereof and mixtures thereof. Specific examples include methanol, ethanol, propanol, dioxane, ethylene glycol, propylene glycol, diethylene glycol, glycerol, dipropylene glycol, tetrahydrofuran, and other water-soluble or water-miscible materials, and mixtures thereof. When mixtures of water and water-soluble or water-miscible organic liquids are selected as the aqueous reaction media, the water to cosolvent weight ratio is typically in the range of about 100:0 to about 10:90.

The (co)polymers of step A) may have a number average molecular weight from 1 000 to 100 000 g/mol, preferably from 1000 to 50 000 g/mol and, more preferably, from 1000 to 20 000 g/mol. The number average molecular weight may be determined by size exclusion chromatography (SEC), matrix assisted laser desorption/ionization mass spectrometry (MALDI-MS) or, if the initiator carries a group which can be easily distinguished from the monomer(s), by NMR spectroscopy or other conventional methods.

The polymers or copolymers of step A) have preferably a polydispersity of from 1.0 to 2.0, more preferably of from 1.1 to 1.8, and most preferably from 1.1 to 1.5.

The temperature applied in the second step is in general between 150° C and 300° C and must be such, that the thermoplastic or elastomeric polymer or copolymer can be processed or mixed in a typical polymer processing device such as a mixer, kneader or extruder.

The reaction time for step B) depends on the reactivity of the macroinitiator and the desired amount of grafted polymer radicals. Typical reaction times are from a few minutes to hours. Preferably the reaction time is from 1 min to 1 h, most preferably from 2 min to 20 min.

When the macroinitiator is added to the thermoplastic or elastomeric polymer or copolymer no additional monomer is added.

The temperature applied in the second reaction step B) depends on the polymer and is for example 50° to 150° C above the glass transition temperature (T_g) for amorphous polymers and 20° to 180° C above the melting temperature (T_m) for semi-crystalline polymers. Typical are following temperatures:

low density polyethylene	LDPE	170-260° C
high density polyethylene	HDPE	180-270° C
polypropylene	PP	180-280° C
polystyrene	PS	190-280° C
styrene-block copolymers	SB(S)	180-260° C
ethylene-propylene-diene modified	EPDM	180-260° C
ethylene propylene rubber	EPR	180-260° C

In a preferred process the temperature in the second step B) is from 170° C to 280° C, more preferred from 190° C to 280° C. The processing temperature shall be adjusted to achieve a homogenous polymer melt and to avoid thermal degradation.

Step B) of the process may be performed in any reactor suitable for mixing a polymer melt. Preferably the reactor is an extruder, mixing or kneading apparatus as for example described in "Handbuch der Kunststoffextrusion" Vol.1, editor F. Hensen, W. Knappe and H. Potente, 1989, pages 3-7. If an extruder is used the process may be described as reactive extrusion process. Examples of reactive extrusion equipment and processes are given by G. H. Hu et al., in "Reactive Modifiers for Polymers", first edition, Blackie Academic & Professional an Imprint of Chapman & Hall, London 1997, chapter 1, pages 1-97.

The addition to the polymer can be effected in any customary mixing apparatus in which the polymer is melted and mixed with the additives. Suitable apparatus are known to those skilled in the art, such apparatus being predominantly mixers, kneaders and extruders.

The process is preferably carried out, by adding the compounds during processing in an extruder.

Especially preferred processing apparatus include single-screw extruders, double-screw extruders with screws rotating in the same or opposite directions, planetary roller extruders, ring extruders or co-kneaders. It is also possible to use processing machines which contain at least one degassing zone and which can be placed under reduced pressure.

Suitable extruders and kneaders are described *inter alia* in *Handbuch der Kunststoffextrusion, Vol. 1 Grundlagen*, Eds. F. Hensen, W. Knappe, H. Potente, 1989, pages 3-7, ISBN:3-446-14339-4 (Vol. 2 *Extrusionsanlagen* 1986, ISBN 3-446-14329-7).

By way of example, the screw length is 1 - 60 times the screw diameter and preferably 35 - 48 times the screw diameter. The screw speed is preferably 10 - 600 revolutions per minute (rev/min) and more especially 25 - 300 rev/min.

The maximum throughput is dependent upon the screw diameter, speed and driving power. The process of the present invention can also be carried out at lower than the maximum throughput by varying the mentioned parameters or by operating with feed-weighing devices.

If a plurality of components is added, these can be added premixed or individually.

The polymers / oligomers are to be exposed to elevated temperature for a sufficient period of time for the desired grafting yield to occur. The temperature is above the softening temperature in the case of amorphous polymers or the melting temperature in the case of crystalline polymers.

Preferably, if an extruder is used, a reduced pressure of less than 200 mbar is applied during extrusion. Volatile byproducts are removed thereby.

Preferably the nitroxyl terminated polymer or oligomer of step A) is added to the thermoplastic or elastomeric polymer or copolymer in an amount from 0.1% to 50% by weight.

Further subjects of the invention are a grafted thermoplastic or elastomeric polymer or copolymer obtained by the above process and the use of a nitroxyl terminated polymer or oligomer for the preparation of a grafted thermoplastic or elastomeric polymer or copolymer comprising heating mixing and reacting the nitroxyl terminated oligomer or polymer together with a thermoplastic or elastic polymer or copolymer at a temperature of between 150° C and 300° C.

There may be further additives added during step B) of the process, such as processing stabilizers, light or heat stabilizers, fillers pigments and the like.

1. Antioxidants

1.1. Alkylated monophenols, for example 2,6-di-tert-butyl-4-methylphenol, 2-tert-butyl-4,6-dimethylphenol, 2,6-di-tert-butyl-4-ethylphenol, 2,6-di-tert-butyl-4-n-butylphenol, 2,6-di-tert-butyl-4-isobutylphenol, 2,6-dicyclopentyl-4-methylphenol, 2-(α -methylcyclohexyl)-4,6-dimethylphenol, 2,6-dioctadecyl-4-methylphenol, 2,4,6-tricyclohexylphenol, 2,6-di-tert-butyl-4-methoxymethylphenol, nonylphenols which are linear or branched in the side chains, for example 2,6-di-nonyl-4-methylphenol, 2,4-dimethyl-6-(1'-methylundec-1'-yl)phenol, 2,4-dimethyl-6-(1'-methylheptadec-1'-yl)phenol, 2,4-dimethyl-6-(1'-methyltridec-1'-yl)phenol and mixtures thereof.

1.2. Alkylthiomethylphenols, for example 2,4-dioctylthiomethyl-6-tert-butylphenol, 2,4-dioctylthiomethyl-6-methylphenol, 2,4-dioctylthiomethyl-6-ethylphenol, 2,6-di-dodecylthiomethyl-4-nonylphenol.

1.3. Hydroquinones and alkylated hydroquinones, for example 2,6-di-tert-butyl-4-methoxyphenol, 2,5-di-tert-butylhydroquinone, 2,5-di-tert-amylhydroquinone, 2,6-diphenyl-4-octadecyloxyphenol, 2,6-di-tert-butylhydroquinone, 2,5-di-tert-butyl-4-hydroxyanisole, 3,5-di-tert-butyl-4-hydroxyanisole, 3,5-di-tert-butyl-4-hydroxyphenyl stearate, bis(3,5-di-tert-butyl-4-hydroxyphenyl) adipate.

1.4. Tocopherols, for example α -tocopherol, β -tocopherol, γ -tocopherol, δ -tocopherol and mixtures thereof (vitamin E).

1.5. Hydroxylated thiodiphenyl ethers, for example 2,2'-thiobis(6-tert-butyl-4-methylphenol), 2,2'-thiobis(4-octylphenol), 4,4'-thiobis(6-tert-butyl-3-methylphenol), 4,4'-thiobis(6-tert-butyl-2-methylphenol), 4,4'-thiobis(3,6-di-sec-amylphenol), 4,4'-bis(2,6-dimethyl-4-hydroxyphenyl)-disulfide.

1.6. Alkylidenebisphenols, for example 2,2'-methylenebis(6-tert-butyl-4-methylphenol), 2,2'-methylenebis(6-tert-butyl-4-ethylphenol), 2,2'-methylenebis[4-methyl-6-(α -methylcyclohexyl)phenol], 2,2'-methylenebis(4-methyl-6-cyclohexylphenol), 2,2'-methylenebis(6-nonyl-4-methylphenol), 2,2'-methylenebis(4,6-di-tert-butylphenol), 2,2'-ethylidenebis(4,6-di-tert-butylphenol), 2,2'-ethylidenebis(6-tert-butyl-4-isobutylphenol), 2,2'-methylenebis[6-(α -methylbenzyl)-4-nonylphenol], 2,2'-methylenebis[6-(α,α -dimethylbenzyl)-4-nonylphenol], 4,4'-methylenebis(2,6-di-tert-butylphenol), 4,4'-methylenebis(6-tert-butyl-2-methylphenol), 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 2,6-bis(3-tert-butyl-5-methyl-2-hydroxybenzyl)-4-methylphenol, 1,1,3-tris(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)-3-n-dodecylmercaptobutane, ethylene glycol bis[3,3-bis(3'-tert-butyl-4'-hydroxyphenyl)butyrate], bis(3-tert-butyl-4-hydroxy-5-methyl-phenyl)dicyclopentadiene, bis[2-(3'-tert-butyl-2'-hydroxy-5'-methylbenzyl)-6-tert-butyl-4-methylphenyl]terephthalate, 1,1-bis-(3,5-dimethyl-2-hydroxyphenyl)butane, 2,2-bis(3,5-di-tert-butyl-4-hydroxyphenyl)propane, 2,2-bis-(5-tert-butyl-4-hydroxy-2-methylphenyl)-4-n-dodecylmercaptobutane, 1,1,5,5-tetra(5-tert-butyl-4-hydroxy-2-methylphenyl)pentane.

1.7. O-, N- and S-benzyl compounds, for example 3,5,3',5'-tetra-tert-butyl-4,4'-dihydroxydibenzyl ether, octadecyl-4-hydroxy-3,5-dimethylbenzylmercaptoacetate, tridecyl-4-hydroxy-3,5-di-tert-butylbenzylmercaptoacetate, tris(3,5-di-tert-butyl-4-hydroxybenzyl)amine, bis(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)dithioterephthalate, bis(3,5-di-tert-butyl-4-hydroxybenzyl)sulfide, isooctyl-3,5-di-tert-butyl-4-hydroxybenzylmercaptoacetate.

1.8. Hydroxybenzylated malonates, for example dioctadecyl-2,2-bis(3,5-di-tert-butyl-2-hydroxybenzyl)malonate, di-octadecyl-2-(3-tert-butyl-4-hydroxy-5-methylbenzyl)malonate, didodecylmercaptoethyl-2,2-bis(3,5-di-tert-butyl-4-hydroxybenzyl)malonate, bis[4-(1,1,3,3-tetramethylbutyl)phenyl]-2,2-bis(3,5-di-tert-butyl-4-hydroxybenzyl)malonate.

1.9. Aromatic hydroxybenzyl compounds, for example 1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl)-2,4,6-trimethylbenzene, 1,4-bis(3,5-di-tert-butyl-4-hydroxybenzyl)-2,3,5,6-tetramethylbenzene, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxybenzyl)phenol.

1.10. Triazine compounds, for example 2,4-bis(octylmercapto)-6-(3,5-di-tert-butyl-4-hydroxyanilino)-1,3,5-triazine, 2-octylmercapto-4,6-bis(3,5-di-tert-butyl-4-hydroxyanilino)-1,3,5-triazine, 2-octylmercapto-4,6-bis(3,5-di-tert-butyl-4-hydroxyphenoxy)-1,3,5-triazine, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxyphenoxy)-1,2,3-triazine, 1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl)isocyanurate, 1,3,5-tris(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)isocyanurate, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxyphenylethyl)-1,3,5-triazine, 1,3,5-tris(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)-hexahydro-1,3,5-triazine, 1,3,5-tris(3,5-dicyclohexyl-4-hydroxybenzyl)isocyanurate.

1.11. Benzylphosphonates, for example dimethyl-2,5-di-tert-butyl-4-hydroxybenzylphosphonate, diethyl-3,5-di-tert-butyl-4-hydroxybenzylphosphonate, dioctadecyl-3,5-di-tert-butyl-4-hydroxybenzylphosphonate, dioctadecyl-5-tert-butyl-4-hydroxy-3-methylbenzylphosphonate, the calcium salt of the monoethyl ester of 3,5-di-tert-butyl-4-hydroxybenzylphosphonic acid.

1.12. Acylaminophenols, for example 4-hydroxylauranilide, 4-hydroxystearanilide, octyl N-(3,5-di-tert-butyl-4-hydroxyphenyl)carbamate.

1.13. Esters of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, n-octanol, i-octanol, octadecanol, 1,6-hexanediol, 1,9-

nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.14. Esters of β -(5-tert-butyl-4-hydroxy-3-methylphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, n-octanol, i-octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane; 3,9-bis[2-{3-(3-tert-butyl-4-hydroxy-5-methylphenyl)propionyloxy}-1,1-dimethylethyl]-2,4,8,10-tetraoxaspiro[5.5]undecane.

1.15. Esters of β -(3,5-dicyclohexyl-4-hydroxyphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.16. Esters of 3,5-di-tert-butyl-4-hydroxyphenyl acetic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.17. Amides of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid e.g. N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hexamethylenediamide, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)trimethylenediamide, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hydrazide, N,N'-bis[2-(3-[3,5-di-tert-butyl-4-hydroxyphenyl]propionyloxy)ethyl]oxamide (Nau-gard®XL-1, supplied by Uniroyal).

1.18. Ascorbic acid (vitamin C)

1.19. Aminic antioxidants, for example N,N'-di-isopropyl-p-phenylenediamine, N,N'-di-sec-butyl-p-phenylenediamine, N,N'-bis(1,4-dimethylpentyl)-p-phenylenediamine, N,N'-bis(1-ethyl-3-methylpentyl)-p-phenylenediamine, N,N'-bis(1-methylheptyl)-p-phenylenediamine, N,N'-dicyclohexyl-p-phenylenediamine, N,N'-diphenyl-p-phenylenediamine, N,N'-bis(2-naphthyl)-p-phenylenediamine, N-isopropyl-N'-phenyl-p-phenylenediamine, N-(1,3-dimethylbutyl)-N'-phenyl-p-phenylenediamine, N-(1-methylheptyl)-N'-phenyl-p-phenylenediamine, N-cyclohexyl-N'-phenyl-p-phenylenediamine, 4-(p-toluenesulfamoyl)diphenylamine, N,N'-dimethyl-N,N'-di-sec-butyl-p-phenylenediamine, diphenylamine, N-allyldiphenylamine, 4-isopropoxydiphenylamine, N-phenyl-1-naphthylamine, N-(4-tert-octylphenyl)-1-naphthylamine, N-phenyl-2-naphthylamine, octylated diphenylamine, for example p,p'-di-tert-octyldiphenylamine, 4-n-butylaminophenol, 4-butyrylamino-phenol, 4-nonanoylamino-phenol, 4-dodecanoylamino-phenol, 4-octadecanoylamino-phenol, bis(4-methoxyphenyl)amine, 2,6-di-tert-butyl-4-dimethylaminomethylphenol, 2,4'-diaminodiphenylmethane, 4,4'-diaminodiphenylmethane, N,N,N',N'-tetramethyl-4,4'-diaminodiphenylmethane, 1,2-bis[(2-methylphenyl)amino]ethane, 1,2-bis(phenylamino)propane, (o-tolyl)biguanide, bis[4-(1',3'-dimethylbutyl)phenyl]amine, tert-octylated N-phenyl-1-naphthylamine, a mixture of mono- and dialkylated tert-butyl/tert-octyldiphenylamines, a mixture of mono- and dialkylated nonyldiphenylamines, a mixture of mono- and dialkylated dodecyldiphenylamines, a mixture of mono- and dialkylated isopropyl/isohexyldiphenylamines, a mixture of mono- and dialkylated tert-butyl/diphenylamines, 2,3-dihydro-3,3-dimethyl-4H-1,4-benzothiazine, phenothiazine, a mixture of mono- and dialkylated tert-butyl/tert-octylphenothiazines, a mixture of mono- and dialkylated tert-octylphenothiazines, N-allylphenothiazine, N,N,N',N'-tetraphenyl-1,4-diaminobut-2-ene, N,N-bis(2,2,6,6-tetramethylpiperid-4-yl)-hexamethylenediamine, bis(2,2,6,6-tetramethylpiperid-4-yl)sebacate, 2,2,6,6-tetramethylpiperidin-4-one, 2,2,6,6-tetramethylpiperidin-4-ol.

2. UV absorbers and light stabilisers

2.1. 2-(2'-Hydroxyphenyl)benzotriazoles, for example 2-(2'-hydroxy-5'-methylphenyl)benzotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(5'-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(2'-hydroxy-5'-(1,1,3,3-tetramethylbutyl)phenyl)benzotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-methylphenyl)-5-chlorobenzotriazole, 2-(3'-sec-butyl-5'-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(2'-

hydroxy-4'-octyloxyphenyl)benzotriazole, 2-(3',5'-di-tert-amyl-2'-hydroxyphenyl)benzotriazole, 2-(3',5'-bis(α,α -dimethylbenzyl)-2'-hydroxyphenyl)benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-octyloxycarbonylethyl)phenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-5'-[2-(2-ethylhexyloxy)carbonylethyl]-2'-hydroxyphenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-methoxycarbonylethyl)phenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-methoxycarbonylethyl)phenyl)benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-octyloxycarbonylethyl)phenyl)benzotriazole, 2-(3'-tert-butyl-5'-[2-(2-ethylhexyloxy)carbonylethyl]-2'-hydroxyphenyl)benzotriazole, 2-(3'-dodecyl-2'-hydroxy-5'-methylphenyl)benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-isooctyloxycarbonylethyl)phenyl)benzotriazole, 2,2'-methylenebis[4-(1,1,3,3-tetramethylbutyl)-6-benzotriazole-2-ylphenol]; the transesterification product of 2-[3'-tert-butyl-5'-(2-methoxycarbonylethyl)-2'-hydroxyphenyl]-2H-benzotriazole with polyethylene glycol 300; $\left[R - CH_2CH_2 - COO - CH_2CH_2 \right]_2$, where $R = 3'$ -tert-butyl-4'-hydroxy-5'-2H-benzotriazol-2-ylphenyl, 2-[2'-hydroxy-3'-(α,α -dimethylbenzyl)-5'-(1,1,3,3-tetramethylbutyl)phenyl]benzotriazole; 2-[2'-hydroxy-3'-(1,1,3,3-tetramethylbutyl)-5'-(α,α -dimethylbenzyl)phenyl]benzotriazole.

2.2. 2-Hydroxybenzophenones, for example the 4-hydroxy, 4-methoxy, 4-octyloxy, 4-decyloxy, 4-dodecyloxy, 4-benzyloxy, 4,2',4'-trihydroxy and 2'-hydroxy-4,4'-dimethoxy derivatives.

2.3. Esters of substituted and unsubstituted benzoic acids, for example 4-tert-butylphenyl salicylate, phenyl salicylate, octylphenyl salicylate, dibenzoyl resorcinol, bis(4-tert-butylbenzoyl)resorcinol, benzoyl resorcinol, 2,4-di-tert-butylphenyl 3,5-di-tert-butyl-4-hydroxybenzoate, hexadecyl 3,5-di-tert-butyl-4-hydroxybenzoate, octadecyl 3,5-di-tert-butyl-4-hydroxybenzoate, 2-methyl-4,6-di-tert-butylphenyl 3,5-di-tert-butyl-4-hydroxybenzoate.

2.4. Acrylates, for example ethyl α -cyano- β,β -diphenylacrylate, isooctyl α -cyano- β,β -diphenylacrylate, methyl α -carbomethoxycinnamate, methyl α -cyano- β -methyl-p-methoxycinnamate, butyl α -cyano- β -methyl-p-methoxycinnamate, methyl α -carbomethoxy-p-methoxycinnamate and N-(β -carbomethoxy- β -cyanovinyl)-2-methylindoline.

2.5. Nickel compounds, for example nickel complexes of 2,2'-thiobis[4-(1,1,3,3-tetramethylbutyl)phenol], such as the 1:1 or 1:2 complex, with or without additional ligands such as n-butylamine, triethanolamine or N-cyclohexyldiethanolamine, nickel dibutyldithiocarbamate,

nickel salts of the monoalkyl esters, e.g. the methyl or ethyl ester, of 4-hydroxy-3,5-di-tert-butylbenzylphosphonic acid, nickel complexes of ketoximes, e.g. of 2-hydroxy-4-methylphenylundecylketoxime, nickel complexes of 1-phenyl-4-lauroyl-5-hydroxypyrazole, with or without additional ligands.

2.6. Sterically hindered amines, for example bis(2,2,6,6-tetramethyl-4-piperidyl)sebacate, bis(2,2,6,6-tetramethyl-4-piperidyl)succinate, bis(1,2,2,6,6-pentamethyl-4-piperidyl)sebacate, bis(1-octyloxy-2,2,6,6-tetramethyl-4-piperidyl)sebacate, bis(1,2,2,6,6-pentamethyl-4-piperidyl) n-butyl-3,5-di-tert-butyl-4-hydroxybenzylmalonate, the condensate of 1-(2-hydroxyethyl)-2,2,6,6-tetramethyl-4-hydroxypiperidine and succinic acid, linear or cyclic condensates of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-tert-octylamino-2,6-dichloro-1,3,5-triazine, tris(2,2,6,6-tetramethyl-4-piperidyl)nitrilotriacetate, tetrakis(2,2,6,6-tetramethyl-4-piperidyl)-1,2,3,4-butanetetracarboxylate, 1,1'-(1,2-ethanediyl)-bis(3,3,5,5-tetramethylpiperazinone), 4-benzoyl-2,2,6,6-tetramethylpiperidine, 4-stearyloxy-2,2,6,6-tetramethylpiperidine, bis(1,2,2,6,6-pentamethylpiperidyl)-2-n-butyl-2-(2-hydroxy-3,5-di-tert-butylbenzyl)-malonate, 3-n-octyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro[4.5]decane-2,4-dione, bis(1-octyloxy-2,2,6,6-tetramethylpiperidyl)sebacate, bis(1-octyloxy-2,2,6,6-tetramethylpiperidyl)succinate, linear or cyclic condensates of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-morpholino-2,6-dichloro-1,3,5-triazine, the condensate of 2-chloro-4,6-bis(4-n-butylamino-2,2,6,6-tetramethylpiperidyl)-1,3,5-triazine and 1,2-bis(3-aminopropylamino)ethane, the condensate of 2-chloro-4,6-di-(4-n-butylamino-1,2,2,6,6-pentamethylpiperidyl)-1,3,5-triazine and 1,2-bis(3-aminopropylamino)ethane, 8-acetyl-3-dodecyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro[4.5]decane-2,4-dione, 3-dodecyl-1-(2,2,6,6-tetramethyl-4-piperidyl)pyrrolidine-2,5-dione, 3-dodecyl-1-(1,2,2,6,6-pentamethyl-4-piperidyl)pyrrolidine-2,5-dione, a mixture of 4-hexadecyloxy- and 4-stearyloxy-2,2,6,6-tetramethylpiperidine, a condensate of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-cyclohexylamino-2,6-dichloro-1,3,5-triazine, a condensate of 1,2-bis(3-aminopropylamino)ethane and 2,4,6-trichloro-1,3,5-triazine as well as 4-butylamino-2,2,6,6-tetramethylpiperidine (CAS Reg. No. [136504-96-6]); a condensate of 1,6-hexanediamine and 2,4,6-trichloro-1,3,5-triazine as well as N,N-dibutylamine and 4-butylamino-2,2,6,6-tetramethylpiperidine (CAS Reg. No. [192268-64-7]); N-(2,2,6,6-tetramethyl-4-piperidyl)-n-dodecylsuccinimide, N-(1,2,2,6,6-pentamethyl-4-piperidyl)-n-dodecylsuccinimide, 2-undecyl-7,7,9,9-tetramethyl-1-oxa-3,8-diaza-4-oxo-spiro[4,5]decane, a reaction product of 7,7,9,9-tetramethyl-2-cycloundecyl-1-oxa-3,8-diaza-4-oxospiro-[4,5]decane and epichlorohydrin, 1,1-bis(1,2,2,6,6-pentamethyl-4-

piperidylloxycarbonyl)-2-(4-methoxyphenyl)ethene, N,N'-bis-formyl-N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine, a diester of 4-methoxymethylenemalononic acid with 1,2,2,6,6-pentamethyl-4-hydroxypiperidine, poly[methylpropyl-3-oxy-4-(2,2,6,6-tetramethyl-4-piperidyl)]siloxane, a reaction product of maleic acid anhydride- α -olefin copolymer with 2,2,6,6-tetramethyl-4-aminopiperidine or 1,2,2,6,6-pentamethyl-4-aminopiperidine.

2.7. Oxamides, for example 4,4'-dioctyloxyoxanilide, 2,2'-diethoxyoxanilide, 2,2'-dioctyloxy-5,5'-di-tert-butoxanilide, 2,2'-didodecyloxy-5,5'-di-tert-butoxanilide, 2-ethoxy-2'-ethyloxanilide, N,N'-bis(3-dimethylaminopropyl)oxamide, 2-ethoxy-5-tert-butyl-2'-ethoxanilide and its mixture with 2-ethoxy-2'-ethyl-5,4'-di-tert-butoxanilide, mixtures of o- and p-methoxy-disubstituted oxanilides and mixtures of o- and p-ethoxy-disubstituted oxanilides.


2.8. 2-(2-Hydroxyphenyl)-1,3,5-triazines, for example 2,4,6-tris(2-hydroxy-4-octyloxyphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2,4-dihydroxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2,4-bis(2-hydroxy-4-propyloxyphenyl)-6-(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(4-methylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-dodecyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-tridecyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-butyloxypropoxy)phenyl]-4,6-bis(2,4-dimethyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-octyloxypropyloxy)phenyl]-4,6-bis(2,4-dimethyl)-1,3,5-triazine, 2-[4-(dodecyloxy/tridecyloxy-2-hydroxypropoxy)-2-hydroxyphenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-dodecyloxypropoxy)phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-hexyloxy)phenyl-4,6-diphenyl-1,3,5-triazine, 2-(2-hydroxy-4-methoxyphenyl)-4,6-diphenyl-1,3,5-triazine, 2,4,6-tris[2-hydroxy-4-(3-butoxy-2-hydroxypropoxy)phenyl]-1,3,5-triazine, 2-(2-hydroxyphenyl)-4-(4-methoxyphenyl)-6-phenyl-1,3,5-triazine, 2-[2-hydroxy-4-[3-(2-ethylhexyl-1-oxy)-2-hydroxypropyloxy]phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine.




3. Metal deactivators, for example N,N'-diphenyloxamide, N-salicylal-N'-salicyloyl hydrazine, N,N'-bis(salicyloyl)hydrazine, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hydrazine, 3-salicyloylamino-1,2,4-triazole, bis(benzylidene)oxalyl dihydrazide, oxanilide, isophthaloyl dihydrazide, sebacoyl bisphenylhydrazide, N,N'-diacetyl adipoyl dihydrazide, N,N'-bis(salicyloyl)oxalyl dihydrazide, N,N'-bis(salicyloyl)thiopropionyl dihydrazide.

4. Phosphites and phosphonites, for example triphenyl phosphite, diphenylalkyl phosphites, phenyldialkyl phosphites, tris(nonylphenyl) phosphite, trilauryl phosphite, trioctadecyl phosphite, distearyl pentaerythritol diphosphite, tris(2,4-di-tert-butylphenyl) phosphite, diisodecyl pentaerythritol diphosphite, bis(2,4-di-tert-butylphenyl) pentaerythritol diphosphite, bis(2,4-di-cumylphenyl) pentaerythritol diphosphite, bis(2,6-di-tert-butyl-4-methylphenyl) pentaerythritol diphosphite, diisodecyloxypentaerythritol diphosphite, bis(2,4-di-tert-butyl-6-methylphenyl) pentaerythritol diphosphite, bis(2,4,6-tris(tert-butylphenyl) pentaerythritol diphosphite, tristea-ryl sorbitol triphosphite, tetrakis(2,4-di-tert-butylphenyl) 4,4'-biphenylene diphosponite, 6-isooctyloxy-2,4,8,10-tetra-tert-butyl-12H-dibenz[d,g]-1,3,2-dioxaphosphocin, bis(2,4-di-tert-butyl-6-methylphenyl)methyl phosphite, bis(2,4-di-tert-butyl-6-methylphenyl)ethyl phosphite, 6-fluoro-2,4,8,10-tetra-tert-butyl-12-methyl-dibenz[d,g]-1,3,2-dioxaphosphocin, 2,2',2''-nitri-lo-[triethyltris(3,3',5,5'-tetra-tert-butyl-1,1'-biphenyl-2,2'-diyl)phosphite], 2-ethylhexyl(3,3',5,5'-te-tra-tert-butyl-1,1'-biphenyl-2,2'-diyl)phosphite, 5-butyl-5-ethyl-2-(2,4,6-tri-tert-butylphenoxy)-1,3,2-dioxaphosphirane.

The following phosphites are especially preferred:

Tris(2,4-di-tert-butylphenyl) phosphite (Irgafos® 168, Ciba-Geigy), tris(nonylphenyl) phosphite,





5. Hydroxylamines, for example N,N-dibenzylhydroxylamine, N,N-diethylhydroxylamine, N,N-dioctylhydroxylamine, N,N-dilaurylhydroxylamine, N,N-ditetradecylhydroxylamine, N,N-dihexadecylhydroxylamine, N,N-dioctadecylhydroxylamine, N-hexadecyl-N-octadecylhydroxylamine, N-heptadecyl-N-octadecylhydroxylamine, N,N-dialkylhydroxylamine derived from hydrogenated tallow amine.

6. Nitrones, for example N-benzyl-alpha-phenylnitrone, N-ethyl-alpha-methylnitrone, N-octyl-alpha-heptylnitrone, N-lauryl-alpha-undecylnitrone, N-tetradecyl-alpha-tridecylnitrone, N-hexadecyl-alpha-pentadecylnitrone, N-octadecyl-alpha-heptadecylnitrone, N-hexadecyl-alpha-heptadecylnitrone, N-octadecyl-alpha-pentadecylnitrone, N-heptadecyl-alpha-heptadecylnitrone, N-octadecyl-alpha-hexadecylnitrone, nitrone derived from N,N-dialkylhydroxylamine derived from hydrogenated tallow amine.

7. Thiosynergists, for example dilauryl thiodipropionate or distearyl thiodipropionate.

8. Peroxide scavengers, for example esters of β -thiodipropionic acid, for example the lauryl, stearyl, myristyl or tridecyl esters, mercaptobenzimidazole or the zinc salt of 2-mercaptobenzimidazole, zinc dibutyldithiocarbamate, dioctadecyl disulfide, pentaerythritol tetrakis(β -dodecylmercapto)propionate.

9. Polyamide stabilisers, for example copper salts in combination with iodides and/or phosphorus compounds and salts of divalent manganese.

10. Basic co-stabilisers, for example melamine, polyvinylpyrrolidone, dicyandiamide, triallyl cyanurate, urea derivatives, hydrazine derivatives, amines, polyamides, polyurethanes, alkali metal salts and alkaline earth metal salts of higher fatty acids, for example calcium stearate, zinc stearate, magnesium behenate, magnesium stearate, sodium ricinoleate and potassium palmitate, antimony pyrocatecholate or zinc pyrocatecholate.

11. Nucleating agents, for example inorganic substances, such as talcum, metal oxides, such as titanium dioxide or magnesium oxide, phosphates, carbonates or sulfates of, preferably, alkaline earth metals; organic compounds, such as mono- or polycarboxylic acids and the salts thereof, e.g. 4-tert-butylbenzoic acid, adipic acid, diphenylacetic acid, sodium succinate or sodium benzoate; polymeric compounds, such as ionic copolymers (ionomers). Especially preferred are 1,3:2,4-bis(3',4'-dimethylbenzylidene)sorbitol, 1,3:2,4-di(paramethyldibenzylidene)sorbitol, and 1,3:2,4-di(benzylidene)sorbitol.

12. Fillers and reinforcing agents, for example calcium carbonate, silicates, glass fibres, glass bulbs, asbestos, talc, kaolin, mica, barium sulfate, metal oxides and hydroxides, carbon black, graphite, wood flour and flours or fibers of other natural products, synthetic fibers.

13. Other additives, for example plasticisers, lubricants, emulsifiers, pigments, rheology additives, catalysts, flow-control agents, optical brighteners, flameproofing agents, antistatic agents and blowing agents.

14. Benzofuranones and indolinones, for example those disclosed in U.S. 4,325,863; U.S. 4,338,244; U.S. 5,175,312; U.S. 5,216,052; U.S. 5,252,643; DE-A-4316611;

DE-A-4316622; DE-A-4316876; EP-A-0589839 or EP-A-0591102 or 3-[4-(2-acetoxyethoxy)-phenyl]-5,7-di-tert-butylbenzofuran-2-one, 5,7-di-tert-butyl-3-[4-(2-stearoyloxyethoxy)phenyl]-benzofuran-2-one, 3,3'-bis[5,7-di-tert-butyl-3-(4-[2-hydroxyethoxy]phenyl)benzofuran-2-one], 5,7-di-tert-butyl-3-(4-ethoxyphenyl)benzofuran-2-one, 3-(4-acetoxy-3,5-dimethylphenyl)-5,7-di-tert-butylbenzofuran-2-one, 3-(3,5-dimethyl-4-pivaloyloxyphenyl)-5,7-di-tert-butylbenzofuran-2-one, 3-(3,4-dimethylphenyl)-5,7-di-tert-butylbenzofuran-2-one, 3-(2,3-dimethylphenyl)-5,7-di-tert-butylbenzofuran-2-one.

The final comb or graft polymers are useful in many applications such as compatibilizers in polymer blends or alloys, adhesion promoters between two different substrates, surface modification agents, nucleating agents, coupling agents between filler and polymer matrix or dispersing agents, material for shaping parts or films.

The polymers prepared by the present invention are particularly useful for following applications:

adhesives, detergents, dispersants, emulsifiers, surfactants, defoamers, adhesion promoters, corrosion inhibitors, viscosity improvers, lubricants, rheology modifiers, thickeners, crosslinkers, paper treatment, water treatment, electronic materials, paints, coatings, photography, ink materials, imaging materials, superabsorbants, cosmetics, hair products, preservatives, biocide materials or modifiers for asphalt, leather, textiles, ceramics and wood.

The following examples illustrate the invention.

Example A1: Grafting of NO-terminated Polystyrene (PS) onto Styrene-Butadiene-Styrene (SBS)


Synthesis of the macroinitiator 1: acetic acid 2,6-diethyl-2,3,6-trimethyl-1-piperidine-terminated-PS (according to step A, a1).

Styrene is distilled under reduced pressure prior to use. In a dry, argon-purged Schlenk tube, 1 mol% nitroxyl ether (compound 101) is dissolved in 45.45 g styrene. The solution is degassed in three consecutive freeze-thaw-cycles and then purged with argon. The stirred solution is then immersed in an oil bath and polymerized at 110°C for 6 hours. After polymerization, residual monomer is removed under vacuum at 70°C and the polymer is

dried at 70°C in vacuum until constant weight is achieved. Molecular weight is determined as described above ($M_n = 4200$ g/mol).

Synthesis of the macroinitiator 2: acetic acid 2,6-diethyl-2,3,6-trimethyl-1-piperidine-terminated-PS (according to step A, a2).

Styrene is distilled under reduced pressure prior to use. In a dry, argon-purged Schlenk tube, 1 mol% of a nitroxyl radical (compound 102) and 0.77 mol% Benzoylperoxide (BPO) as initiator are dissolved in 45.45 g styrene. The solution is degassed in three consecutive freeze-thaw-cycles and then purged with argon. The stirred solution is then immersed in an oil bath and polymerized at 130°C for 6 hours. After polymerization, residual monomer is removed under vacuum at 70°C and the polymer is dried at 70°C in vacuum until constant weight is achieved. Molecular weight is determined as described above ($M_n = 10400$ g/mol).



The compounds are prepared according to example 1 of GB 2 361 235.

Step B)

A mixture of 350 g SBS (Kraton D 1102 CU (Shell)) and 35 g (10%) NO-terminated-polystyrene as given in table 1 is extruded in a twin screw extruder (Haake TW 100) at 200°C at 50 rpm and the resulting polymer is granulated. 10 g of the granulated polymer are dissolved in tetrahydrofuran (THF), precipitated in methanol and dried at 70°C in vacuum until constant weight is achieved.

Molecular weight and molecular weight distribution are determined by size exclusion chromatography (SEC) on a HP 1090 liquid chromatograph (column PSS 1, lengths 60cm, rate 1ml/min, concentration 10 mg polymer in 1 ml THF; software: winGPC / Polymer Standard Services (PSS), Mainz, Germany) using THF as eluent and a column combination calibrated with narrow polystyrene standards (Polymer Laboratories). The polydispersity is calculated from M_n (g/mol) and M_w (g/mol) as $PD = M_w/M_n$. The results are shown in Table 1.

Table 1: Grafting of NO-terminated-PS onto SBS

Example	NO-terminated PS	Mn [g/mol]	Increase of Mn [%]	PD
reference	None	65530	0	1.3
1	10% macroinitiator 1	72320	10.4	1.3
2	10% macroinitiator 2	78290	19.5	1.2

Reference: SBS extruded, 200° C, 50 rpm

Example A2 Grafting of NO-terminated Polystyrene (PS) onto Ethylene-Propylene-Diene Modified (EPDM)

Synthesis of macroinitiator 3: acetic acid 2,6-diethyl-2,3,6-trimethyl-1-piperidine-terminated-PS (according to example A1, step A).

Styrene is distilled under reduced pressure prior to use. In a dry, argon-purged Schlenk tube, 1 mol % nitroxyl ether (compound 101) is dissolved in 45.45 g styrene. The solution is degassed in three consecutive freeze-thaw-cycles and then purged with argon. The stirred solution is then immersed in an oil bath and polymerized at 130°C for 6 hours. After polymerization, residual monomer is removed under vacuum at 70°C and the polymer is dried at 70°C in vacuum until constant weight is achieved. Molecular weight is determined as described above ($M_n = 7300$ g/mol)


Synthesis of macroinitiator 4: Acetic acid 2,6-diethyl-2,3,6-trimethyl-1-piperidine-terminated-PS (according to example A1, step A)

Styrene is distilled under reduced pressure prior to use. In a dry, argon-purged Schlenk tube, 0.1 mol % nitroxyl ether (NOR) is dissolved in 45.45 g styrene. The solution is degassed in three consecutive freeze-thaw-cycles and then purged with argon. The stirred solution is then immersed in an oil bath and polymerized at 130°C for 6 hours. After polymerization, residual monomer is removed under vacuum at 70°C and the polymer is dried at 70°C in vacuum until constant weight is achieved. Molecular weight is determined as described above ($M_n = 27000$ g/mol).

Synthesis of macroinitiator 5: 2,2,6,6-Tetramethyl-4-propoxy-piperidine-terminated-PS (according to example A1, step A)

Styrene is distilled under reduced pressure prior to use. In a dry, argon-purged Schlenk tube, 1 mol% nitroxyl ether (compound 103) is dissolved in 45.45 g styrene. The solution is degassed in three consecutive freeze-thaw-cycles and then purged with argon. The stirred

solution is then immersed in an oil bath and polymerized at 130°C for 6 hours. After polymerization, residual monomer is removed under vacuum at 70°C and the polymer is dried at 70°C in vacuum until constant weight is achieved. Molecular weight is determined as described above ($M_n = 8000$ g/mol).



The compound is prepared in analogy to the preparation described in GB 2 361 235 from commercially available starting materials.

Step B)

350 g EPDM (Buna EP G 3850 (Bayer AG) is reacted together with 35 g (10 %) NO-terminated-polystyrene as given in Table 2 in a kneader (Brabender W50, volume 55 cm³) at 200°C, 40 rpm and 10 min reaction time. 10 g of the resulting polymer were dissolved in 1,2-dichlorobenzene, precipitated in methanol and dried at 70°C in vacuum until constant weight is achieved. The number average molecular weight and the molecular weight distribution are determined by high temperature gel-permeation-chromatography (HT-GPC) with a Waters 150C (5 PS columns of type μ -Styragel 500Å + HT3 + HT4+ HT5 + HT6, temperature 140°C, rate 1 ml/min, calibration with polystyrene standard supplied from Polymer Standard Services (PSS) using trichlorobenzene as eluent. The polydispersity is calculated from M_n (g/mol) and M_w (g/mol) as $PD = M_w/M_n$.

Table 2: Grafting of NO-terminated-PS onto EPDM

Example	NO-terminated PS	M_n [g/mol]	PD
reference	none	12600	17.6
1	10% macroinitiator 1	84600	2.1
2	10% macroinitiator 2	93980	2.2
3	10% macroinitiator 3	83300	2.4

reference : EPDM after 10 min. in the kneader

Example A3 Grafting of NO-terminated Poly-n-Butylacrylate (P-n-BuA) onto Ethylene-Propylene-Diene Modified (EPDM)

Synthesis of macroinitiator 6: 2,6-Diethyl-2,3,6-trimethyl-piperidine-4-ol-terminated P-n-BuA (according to example A1, step A).

n-Butylacrylate is distilled under reduced pressure prior to use. In a dry, argon-purged Schlenk tube, 1 mol% nitroxyl ether (compound 101) is dissolved in 55.9 g n-butylacrylate. The solution is degassed in three consecutive freeze-thaw-cycles and then purged with argon. The stirred solution is then immersed in an oil bath and polymerized at 110°C for 6 hours. After polymerization, residual monomer is removed under vacuum at 30°C and the polymer is dried at 30°C in vacuum until constant weight is achieved. Molecular weight is determined as described above ($M_n = 5800$ g/mol).

Synthesis of macroinitiator 7: 2,6-Diethyl-2,3,6-trimethyl-piperidine-4-ol-terminated P-n-BuA (according to example A1, step A).

n-butylacrylate is distilled under reduced pressure prior to use. In a dry, argon-purged Schlenk tube, 1 mol% nitroxyl ether (compound 101) is dissolved in 55.9 g n-butylacrylate. The solution is degassed in three consecutive freeze-thaw-cycles and then purged with argon. The stirred solution is then immersed in an oil bath and polymerized at 130°C for 24 hours. After polymerization, residual monomer is removed under vacuum at 30°C and the polymer is dried at 30°C in vacuum until constant weight is achieved. Molecular weight is determined as described above ($M_n = 10400$ g/mol).

Step B)

350 g EPDM is reacted in the presence of 35 g (10 %) NO-terminated-poly-n-butylacrylate (see table 3) in a kneader (Brabender W50, volume 55cm³) at 200°C, 40 rpm and 10 min reaction time. 10 g of the resulting polymer were solved in 1,2-Dichlorobenzene, precipitated in Methanol and dried at 70°C in vacuum until constant weight is achieved. The number average molecular weight and the molecular weight distribution are determined by high temperature gel-permeation-chromatography (HT-GPC) with a Waters 150C (5 PS columns of type μ -Styragel 500Å + HT3 + HT4+ HT5 + HT6, temperature 140°C, rate 1ml/min, calibration with polystyrene standard supplied from Polymer Standard Services (PSS) using

trichlorobenzene as eluent . The polydispersity is calculated from M_n (g/mol) and M_w (g/mol) as $PD = M_w/M_n$.

Table 3: Grafting of NO-term.-P-n-BuA onto EPDM

Example	NO-terminated PS	M_n [g/mol]	PD
reference	none	12600	17.6
1	10% macroinitiator 6	64300	3.1
2	10% macroinitiator 7	67000	2.6

reference : EPDM after 10 min. in the kneader

Claims

1. A process for the preparation of a grafted thermoplastic or elastomeric polymer or copolymer, which process comprises in a first step

A) the preparation of a nitroxyl terminated oligomer or polymer by controlled free radical polymerization of an ethylenically unsaturated monomer

a1) in the presence of a nitroxyl ether $R'R''N-O-X$ wherein X is selected such, that cleavage of the O-X bond occurs and a radical $X\bullet$ is formed capable of initiating polymerization; or

a2) in the presence of a nitroxyl radical $R'R''N-O\bullet$ and a free radical initiator capable of initiating polymerization; and in a second step

B) heating, mixing and reacting the nitroxyl terminated oligomer or polymer of step A) together with a thermoplastic or elastomeric polymer or copolymer in the molten state at a temperature of between 150° C and 300° C.


2. A process according to claim 1 wherein the thermoplastic or elastomeric polymer or copolymer is selected from the group consisting of a polyolefin and its copolymers, polystyrene and its block or graft copolymers, polymers and copolymers derived from 1,3-dienes.

3. A process according to claim 2 wherein the thermoplastic or elastomeric polymer or copolymer is selected from the group consisting of



low density polyethylene (LDPE, LLDPE), high density polyethylene (HDPE), polypropylene (PP), polystyrene (PS), styrene-block copolymers (SI(S), SI, SB(S), ABS ASA), ethylene-propylene-diene modified rubber (EPDM, EPM) and ethylene propylene rubber (EPR), polybutylene (PB), polyisobutylene (PIB), poly-4-methylpentene-1 (PMP).

4. A process according to claim 1 wherein the thermoplastic or elastomeric polymer or copolymer contains unsaturated bonds.

5. A process according to claim 1 wherein X is selected from the group consisting of



C₆cycloalkyl)₂CCN, (C₁-C₁₂alkyl)₂CCN, -CH₂CH=CH₂, (C₁-C₁₂)alkyl-CR₂₀-C(O)-(C₁-C₁₂)alkyl, (C₁-C₁₂)alkyl-CR₂₀-C(O)-(C₆-C₁₀)aryl, (C₁-C₁₂)alkyl-CR₂₀-C(O)-(C₁-C₁₂)alkoxy, (C₁-C₁₂)alkyl-CR₂₀-C(O)-phenoxy, (C₁-C₁₂)alkyl-CR₂₀-C(O)-N-di(C₁-C₁₂)alkyl, (C₁-C₁₂)alkyl-CR₂₀-CO-NH(C₁-C₁₂)alkyl, (C₁-C₁₂)alkyl-CR₂₀-CO-NH₂, -CH₂CH=CH-CH₃, -CH₂-C(CH₃)=CH₂,





R₂₀ is hydrogen or C₁-C₁₂alkyl;

the alkyl groups are unsubstituted or substituted with one or more -OH, -COOH or -C(O)R₂₀ groups; and

the aryl groups are phenyl or naphthyl which are unsubstituted or substituted with C₁-C₁₂alkyl, halogen, C₁-C₁₂alkoxy, C₁-C₁₂alkylcarbonyl, glycidyloxy, OH, -COOH or -COO(C₁-C₁₂)alkyl.




6. A process according to claim 1 wherein the nitroxyl-ether or the nitroxyl radical contains a structural element of formula (Ia) or (Ib)






G₁, G₂, G₃, G₄ are independently C₁-C₈alkyl or G₁ and G₂ or G₃ and G₄, or G₁ and G₂ and G₃ and G₄ together form a C₅-C₁₂cycloalkyl group;

G_5, G_6 independently are H, C_1-C_{18} alkyl, phenyl, naphthyl or a group $COOC_1-C_{18}$ alkyl.

7. A process according to claim 6 wherein component a1) and a2) are of formula A, A', B, B' or O, O'





wherein

G₁, G₂, G₃ and G₄ are independently alkyl of 1 to 4 carbon atoms, or G₁ and G₂ together and G₃ and G₄ together, or G₁ and G₂ together or G₃ and G₄ together are pentamethylene;

G₅ and G₆ are independently hydrogen or C₁-C₄ alkyl;

m is 1, 2, 3 or 4

R, if m is 1, is hydrogen, C₁-C₁₈alkyl which is uninterrupted or C₂-C₁₈alkyl which is interrupted by one or more oxygen atoms, cyanoethyl, benzoyl, glycidyl, a monovalent radical of an aliphatic carboxylic acid having 2 to 18 carbon atoms, of a cycloaliphatic carboxylic acid having 7 to 15 carbon atoms, or an α,β-unsaturated carboxylic acid having 3 to 5 carbon atoms or of an aromatic carboxylic acid having 7 to 15 carbon atoms, where each carboxylic acid can be substituted in the aliphatic, cycloaliphatic or aromatic moiety by 1 to 3 -COOZ₁₂ groups, in which Z₁₂ is H, C₁-C₂₀alkyl, C₃-C₁₂alkenyl, C₅-C₇cycloalkyl, phenyl or benzyl; or

R is a monovalent radical of a carbamic acid or phosphorus-containing acid or a monovalent silyl radical;

R, if m is 2, is C₂-C₁₂alkylene, C₄-C₁₂alkenylene, xylylene, a divalent radical of an aliphatic dicarboxylic acid having 2 to 36 carbon atoms, or a cycloaliphatic or aromatic dicarboxylic acid having 8-14 carbon atoms or of an aliphatic, cycloaliphatic or aromatic dicarbamic acid having 8-14 carbon atoms, where each dicarboxylic acid may be substituted in the aliphatic, cycloaliphatic or aromatic moiety by one or two -COOZ₁₂ groups; or

R is a divalent radical of a phosphorus-containing acid or a divalent silyl radical;

R, if m is 3, is a trivalent radical of an aliphatic, cycloaliphatic or aromatic tricarboxylic acid, which may be substituted in the aliphatic, cycloaliphatic or aromatic moiety by

-COOZ₁₂, of an aromatic tricarbamic acid or of a phosphorus-containing acid, or is a trivalent silyl radical,

R, if m is 4, is a tetravalent radical of an aliphatic, cycloaliphatic or aromatic tetracarboxylic acid;

p is 1, 2 or 3,

R₁ is C₁-C₁₂alkyl, C₅-C₇cycloalkyl, C₇-C₈aralkyl, C₂-C₁₈alkanoyl, C₃-C₅alkenoyl or benzoyl;


when p is 1,

R₂ is C₁-C₁₈alkyl, C₅-C₇cycloalkyl, C₂-C₈alkenyl unsubstituted or substituted by a cyano, carbonyl or carbamide group, or is glycidyl, a group of the formula -CH₂CH(OH)-Z or of the formula -CO-Z- or -CONH-Z wherein Z is hydrogen, methyl or phenyl; or

when p is 2,

R₂ is C₂-C₁₂alkylene, C₆-C₁₂-arylene, xylylene, a -CH₂CH(OH)CH₂-O-B-O-CH₂CH(OH)CH₂- group, wherein B is C₂-C₁₀alkylene, C₆-C₁₅arylene or C₆-C₁₂cycloalkylene; or, provided that R₁ is not alkanoyl, alkenoyl or benzoyl, R₂ can also be a divalent acyl radical of an aliphatic, cycloaliphatic or aromatic dicarboxylic acid or dicarbamic acid, or can be the group -CO-; or R₁ and R₂ together when p is 1 can be the cyclic acyl radical of an aliphatic or aromatic 1,2- or 1,3-dicarboxylic acid; or

R₂ is a group






where T₇ and T₈ are independently hydrogen, alkyl of 1 to 18 carbon atoms, or T₇ and T₈ together are alkylene of 4 to 6 carbon atoms or 3-oxapentamethylene;




when p is 3,

R₂ is 2,4,6-triazinyl; and

X is as defined in claim 5.

8. A process according to claim 7 wherein component a1) and a2) are of formula A, A', B, B' or O, O'





wherein

m is 1,

R is hydrogen, C₁-C₁₈alkyl which is uninterrupted or interrupted by one or more oxygen atoms, cyanoethyl, benzoyl, glycidyl, a monovalent radical of an aliphatic carboxylic acid having 2 to 18 carbon atoms, of a cycloaliphatic carboxylic acid having 7 to 15 carbon atoms, or an α,β-unsaturated carboxylic acid having 3 to 5 carbon atoms or of an aromatic carboxylic acid having 7 to 15 carbon atoms;

p is 1;

R₁₀₁ is C₁-C₁₂alkyl, C₅-C₇cycloalkyl, C₇-C₈aralkyl, C₂-C₁₈alkanoyl, C₃-C₅alkenoyl or benzoyl;

R₁₀₂ is C₁-C₁₈alkyl, C₅-C₇cycloalkyl, C₂-C₈alkenyl unsubstituted or substituted by a cyano, carbonyl or carbamide group, or is glycidyl, a group of the formula -CH₂CH(OH)-Z or of the formula -CO-Z or -CONH-Z wherein Z is hydrogen, methyl or phenyl;

G₆ is hydrogen and G₅ is hydrogen or C₁-C₄alkyl,

G₁, G₂, G₃ and G₄ are methyl; or

G₁ and G₃ are methyl and G₂ and G₄ are ethyl or propyl or G₁ and G₂ are methyl and G₃ and G₄ are ethyl or propyl; and

X is selected from the group consisting of

-CH₂-phenyl, CH₃CH-phenyl, (CH₃)₂C-phenyl, (C₅-C₈cycloalkyl)₂CCN, (CH₃)₂CCN, -CH₂CH=CH₂, CH₃CH-CH=CH₂ (C₁-C₄alkyl)CR₂₀-C(O)-phenyl, (C₁-C₄)alkyl-CR₂₀-C(O)-(C₁-

C₄)alkoxy, (C₁-C₄)alkyl-CR₂₀-C(O)-(C₁-C₄)alkyl, (C₁-C₄)alkyl-CR₂₀-C(O)-N-di(C₁-C₄)alkyl, (C₁-C₄)alkyl-CR₂₀-C(O)-NH(C₁-C₄)alkyl, (C₁-C₄)alkyl-CR₂₀-C(O)-NH₂, wherein R₂₀ is hydrogen or (C₁-C₄)alkyl.

9. A process according to claim 7 wherein G₂ and G₄ are ethyl, G₁ and G₃ are methyl, G₆ is hydrogen and G₅ is methyl.

10. A process according to claim 1 wherein the free radical initiator of component a2) is a bis-azo compound, a peroxide, a perester or a hydroperoxide.

11. A process according to claim 1, wherein the nitroxylether of component a1) or the nitroxyl radical of component a2) is present in an amount of from 0.001 mol-% to 20 mol-%, based on the monomer or monomer mixture.

12. A process according to claim 1, wherein the free radical initiator is present in an amount of from 0.001 mol-% to 20 mol-%, based on the monomer or monomer mixture.

13. A process according to claim 1, wherein the ethylenically unsaturated monomer or oligomer is selected from the group consisting of styrene, substituted styrene, conjugated dienes, vinyl acetate, vinylpyrrolidone, vinylimidazole, maleic anhydride, (alkyl)acrylic acidanhydrides, (alkyl)acrylic acid salts, (alkyl)acrylic esters, (meth)acrylonitriles, (alkyl)acrylamides, vinyl halides or vinylidene halides.

14. A process according to claim 12, wherein the ethylenically unsaturated monomer is a compound of formula CH₂=C(R_a)-(C=Z)-R_b, wherein R_a is hydrogen or C₁-C₄alkyl, R_b is NH₂, O⁻(Me⁺), glycidyl, unsubstituted C₁-C₁₈alkoxy, C₂-C₁₀₀alkoxy interrupted by at least one N and/or O atom, or hydroxy-substituted C₁-C₁₈alkoxy, unsubstituted C₁-C₁₈alkylamino, di(C₁-C₁₈alkyl)amino, hydroxy-substituted C₁-C₁₈alkylamino or hydroxy-substituted di(C₁-C₁₈alkyl)amino, -O-CH₂-CH₂-N(CH₃)₂ or -O-CH₂-CH₂-N⁺H(CH₃)₂ An⁻; An⁻ is a anion of a monovalent organic or inorganic acid; Me is a monovalent metal atom or the ammonium ion. Z is oxygen or sulfur.

15. A process according to claim 1 wherein step B) is performed in an extruder, mixer or kneading apparatus.

16. A process according to claim 1 wherein the nitroxyl terminated polymer or oligomer of step A) has an average molecular weight of from 1000 to 100 000 Dalton.

17. A process according to claim 1 wherein the nitroxyl terminated polymer or oligomer of step A) has a polydispersity PD from 1.0 to 2.0.

18. A process according to claim 1 wherein the nitroxyl terminated polymer or oligomer of step A) is added to the thermoplastic or elastomeric polymer or copolymer in an amount from 0.1% to 50% by weight.

19. A grafted thermoplastic or elastomeric polymer or copolymer obtained according to claim 1.

20. Use of a nitroxyl terminated polymer or oligomer for the preparation of a grafted thermoplastic or elastomeric polymer or copolymer comprising heating mixing and reacting the nitroxyl terminated oligomer or polymer together with a thermoplastic or elastic polymer or copolymer at a temperature of between 150° C and 300° C.

Abstract

The instant invention relates to a process for the preparation of grafted polymers wherein in a first step A) a oligomer or polymer is prepared by controlled radical polymerization in the presence of a stable free nitroxyl radical or a nitroxylether to obtain a nitroxyl terminated oligomer or polymer and in a second step B) the nitroxyl terminated oligomer or polymer is mixed and reacted with a thermoplastic or elastomeric polymer or copolymer in its molten state at a temperature at which cleavage of the nitroxyl-polymer/oligomer bond occurs, whereby the nitroxyl terminated oligomer or polymer is grafted onto the thermoplastic or elastomeric polymer. A further subject of the present invention is a grafted polymer prepared by said process.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.